



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

Penetration Grade 10/20

| | | |
|---|---------|--------|
| Penetration @ 25 deg. C. | 10/20 | D.5 |
| Softening Point deg. C. | 65/75 | D.36 |
| Ductility @ 25 deg. C. | 5 | D.113 |
| Loss on heating PCT. WT. | 0.5 max | D.6 |
| Drop in penetration after heating PCT. | 25 | D.5 |
| Flash point deg. C. | 250 min | D.92 |
| Solubility in Trichloroethylene | 99 min | D.2042 |



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com