



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

Penetration Grade 20/30

Penetration @ 25 deg. C.	20/30	D.5
Softening Point deg. C.	58/68	D.36
Ductility @ 25 deg. C.	25	D.113
Loss on heating PCT. WT.	0.5 max	D.6
Drop in penetration after heating PCT.	25	D.5
Flash point deg. C.	250 min	D.92
Solubility in Trichloroethylene	99 min	D.2042



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com