



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

Penetration Grade 6/12

Penetration @ 25 deg. C.	6/12	D.5
Softening Point deg. C.	80/90	D.36
Ductility @ 25 deg. C.	-	D.113
Loss on heating PCT. WT.	0.1 max	D.6
Drop in penetration after heating PCT.	-	D.5
Flash point deg. C.	290 min	D.92
Solubility in Trichloroethylene	99 min	D.2042



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com