



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

Oxidized Bitumen R85/25

Specific Gravity @ 25/25 deg. C.	approx 1.05	D.70
Penetration @ 25 deg. C.	10/20	D.5
Softening Point deg. C.	85/95	D.36
Ductility @ 25 deg. C.	1.5 min	D.113
Loss on heating PCT. WT.	0.2 max	D.6
Flash point deg. C.	225 min	D.92
Solubility in Trichloroethylene	99 max	D.4



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com