



AVIN SHIMI JAHAN

Avin Chemistry
General Trading Company
Iranian Bitumen Exporter

Oxidized Bitumen R90/15

| | | |
|---|-------------|-------|
| Specific Gravity @ 25/25 deg. C. | approx 1.05 | D.70 |
| Penetration @ 25 deg. C. | 20/30 | D.5 |
| Softening Point deg. C. | 80/90 | D.36 |
| Ductility @ 25 deg. C. | 30 min | D.113 |
| Loss on heating PCT. WT. | 0.2 max | D.6 |
| Flash point deg. C. | 225 min | D.92 |
| Solubility in Trichloroethylene | 99 max | D.4 |



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St,
Shahid Beheshti Av. Tehran - Iran



+98 - 21 - 88 17 08 22 - 7



+98 - 21 -88 17 08 28



+98 -912 - 220 13 95



info@avinchemistry.com