

MC30 Cutback Bitumen

MC30 Specifications

Priming of all non-bituminous road bases

Typical Physical & Performance Properties

Typical Tilysical & Terrormance Troperaes		
	MC30	
Application Rate	From 0,6 litre per m2 to 1,2 litre/m2	
Spraying/Application Temperature	45° - 65° C	
Ductility @ 25 deg. C.	100 min	
Appearance	Black	
Distillate, % by Vol. of Total Distillate to 360 C	Min	Max
to 190° C	0	15
to 225° C	15	60
to 260° C	50	85
to 316° C	80	100
Residue from Distillation to 360øC, % Vol. of Original Sample	Min	Max
Penetration at 25øC on Residue from Distillation	90	180



Unit 11, 4th Floor, No.22, 6th Alley, Ahmad Ghasir St, Shahid Beheshti Av. Tehran - Iran



(+98 - 21 - 88 17 08 22 - 7



+98 -912 - 220 13 95



+98 - 21 -88 17 08 28